

Logco-break

Bar Bond-Breaking Compound

Description **Logco-break** is a bituminous solution designed to provide a thick film on dowel bars. Once dry and the concrete cast, movement is achieved between the bar and the surrounding concrete. **Logco-break** meets the performance REQUIREMENTS OF Clause 2605 of the D.O.E Specification for Roads and Bridge Works 1969 109.

Application Apply to dowel bars by brush or by dipping, allowing for a maximum of 10 days between coating and casting of concrete. Although satisfactory performance will be obtained at up to 16 days between coating and casting a programmed time limit of 10 days is suggested to allow for un-programmed delays which may occur under site conditions. Re-coating will be required if it is beyond 16 days. During cold weather thickening of **Logco-break** will occur but do not thin. If difficult to apply slightly warm material by the application of indirect heat.

Clean Tools & Equipment Tools and equipment may be cleaned with **Sitewash** supplied by Logco.

Technical Data	Type:	Bitumen
	Colour:	Black
	Solvents:	Petroleum Spirit
	Specific gravity:	0.92
	Flash Point:	39°C
	Average Coverage:	1.8—3.6 m ² / litre Experience shows that is advisable to calculate on the basis of 1 litre to coat a 35 metre length of 25mm bar or a 43 metre length of 20mm bar 12 months min.
	Shelf life:	12 months minimum.



L

Health & Safety

Rubber gloves and goggles should be worn. If in contact with the skin occurs, wash affected areas with proprietary hand cleanser. Eye contamination must be immediately washed with copious amounts of water and medical advice sought.

Packaging

Logco-break is supplied in 5 litre containers.

Storage

Store under dry conditions at ambient temperature and away from direct heat.

O

G

C

O